



Quartz Broadcast Flooring

SYSTEM FAMILY

Resin flooring / application methodology

TYPE

Coloured-quartz broadcast epoxy system

NOMINAL BUILD

3–6 mm

1. SCOPE & SYSTEM DESCRIPTION

This Application Data Sheet describes POLYZEN's method for installing a **coloured-quartz broadcast floor** — a dense, textured, hard-wearing and hygienic floor for wet-process and hygiene-sensitive areas.

It is a **brand-flexible application guide** applicable with a POLYZEN system product or a client-approved equivalent of the same type.

2. SUBSTRATE REQUIREMENTS

- New concrete cured a minimum of 28 days; sound and structurally stable.
- Compressive strength typically ≥ 25 N/mm² and surface tensile (pull-off) ≥ 1.5 N/mm² (indicative; per project).
- Falls, drainage and movement / isolation joints identified and detailed before starting.
- Substrate dry and free of oil, grease, curing compounds and previous coatings.

3. SURFACE PREPARATION

- Mechanically prepare by diamond grinding or captive shot-blasting to a clean, open profile (typical CSP 2–3). Acid etching is not accepted.
- Remove laitance, contamination and unsound material; repair cracks, spalls and joints with compatible epoxy repair mortars.
- Assess substrate moisture per **ASTM F2170** (in-situ RH); apply a moisture-mitigation primer where readings exceed the selected system's limit.
- Vacuum the prepared surface immediately before priming.

4. ENVIRONMENTAL CONDITIONS

- Substrate & ambient temperature 10–35 °C; substrate ≥ 3 °C above dew point throughout application and initial cure.
- Relative humidity within the selected material's limits; do not apply in falling temperatures.
- Protect the area from dust, water, direct sunlight and traffic during application and cure.

5. MATERIALS

Materials: POLYZEN coloured-quartz broadcast system (**ZENDÉCOR Quartz ZD-Q**) — primer, body and any seal/top coat from one compatible system — **or a client-approved equivalent** of the specified type meeting the project specification and standards. Exact mix ratios, consumption, film thickness and cure times are per the **selected material's Technical Data Sheet**.

6. MIXING

- Pre-condition components to 15–25 °C.
- Power-mix the resin, add the hardener and mix thoroughly, then add graded filler/aggregate (where used) to a homogeneous, lump-free, streak-free consistency with a low-speed mixer.
- Mix full kits only, exactly as supplied — no part-mixing, no site additions of solvent or water. Respect the material's pot life.

7. APPLICATION PROCEDURE

- **Prime:** apply epoxy primer.
- **Base + broadcast:** apply the epoxy base coat and broadcast coloured quartz to refusal.
- **Cure & vacuum:** cure, then remove loose quartz by vacuum/sweeping.
- **Grout & seal:** apply epoxy grout and seal coat(s) to consolidate the quartz to the chosen texture and cleanability.

8. COVERAGE, COATS & THICKNESS

- Primer ~0.3-0.4 kg/m²; base + quartz + grout/seal system-based per thickness (indicative).
- Per the selected material's TDS.

9. CURING & RETURN TO SERVICE

- Light foot traffic typically ~24 h at 25 °C (indicative).
- Return to service / wheeled traffic typically ~48-72 h at 25 °C (indicative).
- Full mechanical & chemical cure typically ~7 days at 25 °C (indicative). Cure times extend at lower temperatures — always per the selected material's data sheet.

10. FINISHING & DETAILING

- Integral coving for hygiene detailing.
- Inherent anti-slip texture; slip evaluated per ANSI A326.3 / ASTM E303.

11. QUALITY-CONTROL CHECKPOINTS

- Record substrate moisture (ASTM F2170), temperature and dew point before each application.
- Verify surface profile, cleanliness and primer coverage.
- Check wet-film / applied thickness during placement.
- Spot-check adhesion and visual finish; log ambient conditions through cure.

12. DO'S & DON'TS

Do

- Respect pot life and overcoat windows.
- Maintain a wet edge and continuous bays.
- Control temperature, dust and dew point.
- Follow the selected material's data sheet for ratios & cure.

Don't

- Don't add solvent or water to thin the mix.
- Don't apply over damp or contaminated substrate.
- Don't exceed pot life or apply below dew point.
- Don't mix products from different systems.

13. CLEANING & MAINTENANCE

- Allow full cure before wet cleaning.
- Routine: dust-mop and neutral-pH auto-scrub; avoid harsh abrasives and aggressive solvents.
- Renew the seal coat periodically in high-traffic areas to extend service life.

14. HEALTH, SAFETY & ENVIRONMENT

- Uncured epoxy resins and amine hardeners can cause skin/eye irritation and sensitisation — wear chemical-resistant gloves, goggles and protective clothing.
- Ensure adequate ventilation during mixing and application; control spills and prevent uncured material entering drains.
- Refer to the selected material's Safety Data Sheet (SDS) for full handling, first-aid, spill and disposal information.

POLYZEN INDIA PVT. LTD.

Plot No. 7 & 8, S V Heights, Haritha Vanam Colony Road, Bachupally, Hyderabad, Telangana – 500090
Phone / WhatsApp: 9640126496 | Email: info@polyzen.in | Web: polyzen.in

Disclaimer: this interim Application Data Sheet describes POLYZEN's typical application methodology for this class of system and is provided in good faith. It is a brand-flexible application guide; exact mix ratios, consumption, film thickness and cure times are governed by the selected material's data sheet. All parameters are typical/indicative and are confirmed in the project-specific Method Statement. POLYZEN reserves the right to revise this document; the latest version supersedes all previous.