



ZENDÉCOR Quartz ZD-Q

RANGE

ZENDÉCOR (Decorative)

MATERIAL FAMILY / GROUP

Decorative epoxy / quartz broadcast

CHEMISTRY

coloured-quartz broadcast epoxy system

1. PRODUCT DESCRIPTION

ZENDÉCOR Quartz ZD-Q is a heavy-duty decorative system in which coloured quartz granules are broadcast into an epoxy base and sealed to create a dense, textured, hard-wearing and hygienic floor.

The quartz build offers excellent abrasion and impact resistance with an inherent anti-slip texture, suiting hygiene-sensitive and wet-process areas. Installed by POLYZEN as a complete system.

2. SYSTEM (LAYER BUILD)

The ZENDÉCOR Quartz system is applied by POLYZEN as one integrated installation:

LAYER	FUNCTION	DESCRIPTION
1 — Primer / Base Coat	Adhesion & quartz bed	Epoxy base coat into which coloured quartz is broadcast to refusal.
2 — Quartz Broadcast	Wear texture	Graded coloured quartz broadcast, cured and vacuumed.
3 — Grout / Seal Coat(s)	Consolidation & finish	Epoxy grout and seal coats consolidating the quartz to the chosen texture and cleanability.

3. TYPICAL APPLICATIONS & SECTORS

- Commercial & industrial kitchens
- Food & Beverage wet areas
- Sanitary & wash-down zones
- Healthcare & laboratories
- Changing & shower areas
- Education & institutional

4. KIT COMPOSITION

COMPONENT	DESCRIPTION
Part A — Resin	Bisphenol-A epoxy base / grout
Part B — Hardener	Cycloaliphatic amine curing agent
Coloured Quartz	Graded coloured quartz aggregate
Seal Coat	Epoxy / PU seal

Supplied as a pre-measured multi-part kit. Mix full kits only, exactly as supplied — no part-mixing, no site additions. Kit pack size: **to be confirmed**. The formulation is proprietary to POLYZEN and is not disclosed.

5. TYPICAL / INDICATIVE PROPERTIES

Typical / indicative values — not a guaranteed specification; confirmed against POLYZEN batch testing & project commissioning.

PROPERTY	TEST METHOD	TYPICAL / INDICATIVE VALUE
Finish	—	Quartz broadcast, textured, hard-wearing (anti-slip)
Solids content	—	High-solids / solvent-free class (indicative)
Applied thickness	—	~3-6 mm system (indicative)
Coverage / consumption	—	system-based; per project specification (indicative)
Pot life (mixed kit)	—	~25-40 min at 25 °C (indicative; shorter when warmer)
Overcoat interval	—	~12-24 h at 25 °C (indicative)
Light foot traffic	—	~24 h at 25 °C (indicative)
Full mechanical / chemical cure	—	~7 days at 25 °C (indicative)
Application temperature	—	10-35 °C; substrate ≥ 3 °C above dew point (indicative)
Substrate moisture	ASTM F2170	Within system limits per project assessment (indicative)
Hardness, Shore D	ASTM D2240	~78-85 (indicative)
Compressive strength	ASTM C579	~50-70 MPa (indicative)
Pull-off adhesion to concrete	ASTM D4541	>1.5 N/mm ² , typically cohesive failure in concrete (indicative)
Abrasion resistance (Taber)	ASTM D4060	~50-90 mg loss, CS-17, 1 kg, 1000 cycles (indicative)
Chemical resistance	ASTM C267	Resists dilute household & process chemicals; sealed finish aids cleanability (indicative)
VOC content	—	Low-VOC / solvent-free class (indicative)

6. SURFACE PREPARATION

- **Concrete age & strength:** new concrete cured a minimum of 28 days; sound, structurally stable substrate of adequate strength for the intended service.
- **Mechanical preparation:** diamond grinding or captive shot-blasting to remove laitance, curing compounds and contamination, producing a clean, open-textured profile. Acid etching is not accepted.
- **Moisture:** substrate assessed per ASTM F2170 (in-situ RH) before application; moisture-mitigation primer specified where readings exceed system limits.
- **Repairs:** cracks, joints and defects repaired with compatible epoxy repair mortars before priming.
- **Priming:** full-coverage primer applied to the prepared substrate; the body coat is applied within the primer's overcoat window.

7. APPLICATION (OVERVIEW)

- **Mixing:** pre-condition kits to 15-25 °C. Power-mix components in sequence to a homogeneous, lump-free consistency using a low-speed mixer. Mix full kits only, exactly as supplied.
- **Placement:** apply by the specified method (roller / squeegee-and-backroll / notched trowel + spike-roll) at the stated rate; maintain a wet edge.
- **Intervals:** respect pot life, overcoat windows and cure times; plan pours in continuous bays to avoid day joints in visual areas.
- **Environment:** control ventilation, dust and direct sunlight during application and initial cure; protect from water and contamination until full cure.

A full project-specific Method Statement (bay layout, joint detailing, coving, quality checkpoints) is issued by POLYZEN for every installation.

8. STANDARDS & COMPLIANCE

The ZENDÉCOR Quartz system supports compliance with the following (subject to system design, project detailing & site testing):

- **Performance test methods:** ASTM C579 (compressive), ASTM D4541 (pull-off adhesion), ASTM D4060 (Taber abrasion), ASTM C267 (chemical resistance), ASTM D2240 (Shore hardness), ASTM F2170 (substrate relative humidity).
- **Hygiene-critical environments:** supports compliance with facility requirements under FSSAI and HACCP frameworks (Food & Beverage), and WHO-GMP, EU-GMP Annex 1, US FDA cGMP 21 CFR 211 and Revised Schedule M (Pharmaceutical & Life Sciences), through its seamless, non-dusting, cleanable finish — subject to overall facility design and validation.
- **Slip resistance (where a textured finish is specified):** evaluated per ANSI A326.3 (DCOF) and ASTM E303 (pendulum), subject to system design, footwear & site testing.

9. PACKAGING, STORAGE & SAFETY

- **Packaging:** pre-measured multi-part kits. Pack size: **to be confirmed**.
- **Storage:** keep in original sealed containers, off the ground, in a dry covered area at 5–30 °C, away from direct sunlight, heat and moisture. Shelf life per batch labelling.
- **Safety:** uncured resins and hardeners can cause skin/eye irritation and sensitisation. Wear PPE (chemical-resistant gloves, goggles, protective clothing); ensure ventilation. Do not allow uncured material to enter drains.
- **SDS:** refer to the product Safety Data Sheet before use.

POLYZEN INDIA PVT. LTD.

Plot No. 7 & 8, S V Heights, Haritha Vanam Colony Road, Bachupally, Hyderabad, Telangana – 500090

Phone / WhatsApp: 9640126496 | Email: info@polyzen.in | Web: polyzen.in

Doc Ref: POLYZEN/TDS/ZD-Q

Interim v1 | 2026

ZENDÉCOR Quartz — Quartz / Granule Broadcast Floor

Disclaimer: this interim Technical Data Sheet is given in good faith based on POLYZEN's current knowledge of this class of product. All values are typical / indicative only and do not constitute a guaranteed specification, warranty or certification. Final performance depends on substrate condition, system design, workmanship and service conditions, and is confirmed through POLYZEN batch testing and project commissioning. POLYZEN reserves the right to revise this document; the latest version supersedes all previous.