



ZENDÉCOR Veina ZD-V

RANGE

ZENDÉCOR (Decorative)

MATERIAL FAMILY / GROUP

Decorative epoxy / veined-marble

CHEMISTRY

marble / veined epoxy decorative system

1. PRODUCT DESCRIPTION

ZENDÉCOR Veina ZD-V is a decorative epoxy system that reproduces natural marble and veined-stone effects in a seamless, jointless floor. Veins are hand-worked for a bespoke, luxurious appearance.

Sealed with a clear top coat for wear and cleanability, Veina delivers a high-end aesthetic with the maintenance advantages of seamless resin. Installed by POLYZEN designer-applicator teams.

2. SYSTEM (LAYER BUILD)

The ZENDÉCOR Veina system is applied by POLYZEN as one integrated installation:

LAYER	FUNCTION	DESCRIPTION
1 — Primer Coat	Adhesion	Epoxy primer sealing the prepared substrate.
2 — Decorative Base / Media	Appearance layer	Pigmented epoxy base carrying the decorative media (metallic / veined / flake / quartz) worked to the chosen effect.
3 — Clear Seal / Top Coat	Protection & gloss	Clear epoxy or UV-stable PU seal coat(s) for wear resistance, gloss and cleanability; anti-slip texture optional.

A UV-stable PU seal is recommended for daylight-exposed areas to reduce ambering.

3. TYPICAL APPLICATIONS & SECTORS

- Hospitality & luxury retail
- Lobbies & reception areas
- Corporate & commercial interiors
- Showrooms & experience centres
- Premium residential
- Restaurants & cafés

4. KIT COMPOSITION

COMPONENT	DESCRIPTION
Part A — Resin	Clear/pigmented bisphenol-A epoxy base
Part B — Hardener	Cycloaliphatic amine curing agent
Veining Media	Pigment dispersions for veined effect
Seal Coat	Clear epoxy or UV-stable PU seal

Supplied as a pre-measured multi-part kit. Mix full kits only, exactly as supplied — no part-mixing, no site additions. Kit pack size: **to be confirmed**. The formulation is proprietary to POLYZEN and is not disclosed.

5. TYPICAL / INDICATIVE PROPERTIES

Typical / indicative values — not a guaranteed specification; confirmed against POLYZEN batch testing & project commissioning.

PROPERTY	TEST METHOD	TYPICAL / INDICATIVE VALUE
Finish	—	Veined marble-effect, seamless, high-gloss
Solids content	—	High-solids / solvent-free class (indicative)
Applied thickness	—	~1.5-2 mm system (indicative)
Coverage / consumption	—	system-based; per project specification (indicative)
Pot life (mixed kit)	—	~25-40 min at 25 °C (indicative; shorter when warmer)
Overcoat interval	—	~12-24 h at 25 °C (indicative)
Light foot traffic	—	~24 h at 25 °C (indicative)
Full mechanical / chemical cure	—	~7 days at 25 °C (indicative)
Application temperature	—	10-35 °C; substrate ≥ 3 °C above dew point (indicative)
Substrate moisture	ASTM F2170	Within system limits per project assessment (indicative)
Hardness, Shore D	ASTM D2240	~78-85 (indicative)
Compressive strength	ASTM C579	~50-70 MPa (indicative)
Pull-off adhesion to concrete	ASTM D4541	>1.5 N/mm ² , typically cohesive failure in concrete (indicative)
Abrasion resistance (Taber)	ASTM D4060	~50-90 mg loss, CS-17, 1 kg, 1000 cycles (indicative)
Chemical resistance	ASTM C267	Resists dilute household & process chemicals; sealed finish aids cleanability (indicative)
VOC content	—	Low-VOC / solvent-free class (indicative)

6. SURFACE PREPARATION

- **Concrete age & strength:** new concrete cured a minimum of 28 days; sound, structurally stable substrate of adequate strength for the intended service.
- **Mechanical preparation:** diamond grinding or captive shot-blasting to remove laitance, curing compounds and contamination, producing a clean, open-textured profile. Acid etching is not accepted.
- **Moisture:** substrate assessed per ASTM F2170 (in-situ RH) before application; moisture-mitigation primer specified where readings exceed system limits.
- **Repairs:** cracks, joints and defects repaired with compatible epoxy repair mortars before priming.
- **Priming:** full-coverage primer applied to the prepared substrate; the body coat is applied within the primer's overcoat window.

7. APPLICATION (OVERVIEW)

- **Mixing:** pre-condition kits to 15-25 °C. Power-mix components in sequence to a homogeneous, lump-free consistency using a low-speed mixer. Mix full kits only, exactly as supplied.
- **Placement:** apply by the specified method (roller / squeegee-and-backroll / notched trowel + spike-roll) at the stated rate; maintain a wet edge.
- **Intervals:** respect pot life, overcoat windows and cure times; plan pours in continuous bays to avoid day joints in visual areas.
- **Environment:** control ventilation, dust and direct sunlight during application and initial cure; protect from water and contamination until full cure.

A full project-specific Method Statement (bay layout, joint detailing, coving, quality checkpoints) is issued by POLYZEN for every installation.

8. STANDARDS & COMPLIANCE

The ZENDÉCOR Veina system supports compliance with the following (subject to system design, project detailing & site testing):

- **Performance test methods:** ASTM C579 (compressive), ASTM D4541 (pull-off adhesion), ASTM D4060 (Taber abrasion), ASTM C267 (chemical resistance), ASTM D2240 (Shore hardness), ASTM F2170 (substrate relative humidity).
- **Slip resistance (where a textured finish is specified):** evaluated per ANSI A326.3 (DCOF) and ASTM E303 (pendulum), subject to system design, footwear & site testing.

9. PACKAGING, STORAGE & SAFETY

- **Packaging:** pre-measured multi-part kits. Pack size: **to be confirmed**.
- **Storage:** keep in original sealed containers, off the ground, in a dry covered area at 5–30 °C, away from direct sunlight, heat and moisture. Shelf life per batch labelling.
- **Safety:** uncured resins and hardeners can cause skin/eye irritation and sensitisation. Wear PPE (chemical-resistant gloves, goggles, protective clothing); ensure ventilation. Do not allow uncured material to enter drains.
- **SDS:** refer to the product Safety Data Sheet before use.

POLYZEN INDIA PVT. LTD.

Plot No. 7 & 8, S V Heights, Haritha Vanam Colony Road, Bachupally, Hyderabad, Telangana – 500090
Phone / WhatsApp: 9640126496 | Email: info@polyzen.in | Web: polyzen.in

Doc Ref: POLYZEN/TDS/ZD-V

Interim v1 | 2026

ZENDÉCOR Veina — Marble / Veined Epoxy Floor

Disclaimer: this interim Technical Data Sheet is given in good faith based on POLYZEN's current knowledge of this class of product. All values are typical / indicative only and do not constitute a guaranteed specification, warranty or certification. Final performance depends on substrate condition, system design, workmanship and service conditions, and is confirmed through POLYZEN batch testing and project commissioning. POLYZEN reserves the right to revise this document; the latest version supersedes all previous.